



By Appointment to Her Majesty Queen Elizabeth II  
Manufacturers of French Polishes, Stains and Wax Polishes  
John Myland Limited, London

# MYLANDS

ESTABLISHED LONDON 1884

## PRODUCT DATA SHEETS SPRAY WAX

<b>General</b>	Mylands Spray wax will apply through all cold wax spray units and offers the perfect application with minimum effort.		
<b>Product Codes</b>	<p><b>Product Colour</b></p> <p>Clear Spray Wax (T.F.) Antique Brown Spray Wax Dark Brown Spray Wax Dark Oak Spray Wax (T.F.) Dark Pine Spray Wax K Brown Spray Wax (T.F.) Light Pine Spray Wax (T.F.) Old Pine Spray Wax (T.F.) Rustic Brown Spray Wax Rustic Pine Spray Wax Stripped Pine M7 Spray Wax (T.F.) indicates Toluene Free</p>	<p><b>Product Code Winter Blend</b></p> <p>16 787 8200 16 787 8474 16 787 8215 16 787 8245 16 787 8510 16 787 8251 16 787 8480 16 787 8485 16 787 8210 16 787 8525 16 787 8241</p>	<p><b>Product Code Summer Blend</b></p> <p>N/A 16 787 8473 N/A N/A N/A 16 787 8250 N/A 16 787 8484 N/A N/A 16 787 8240</p>
<b>Technical Data</b>	<p>Spray Wax has been formulated to apply through all cold wax spray units (airless), which makes for easier/faster application without the hard work of hand application.</p> <p>With the more popular colours there is a summer and winter version to allow greater flexibility in variation of ambient conditions.</p> <p>The solvent blends have been formulated to give sufficient 'open' time for buffing after application, about 5 – 10 minutes at 20°C.</p> <p>When buffed the wax gives a perfect shine.</p>		
<b>Application</b>	<p>This wax is formulated to spray through cold wax spray units, but may also be applied by brush or rag if required. However Mylands have other ranges of waxes more suited for manual application – Traditional Wax Polish, Toluene-free Waxes or Toluene Based Waxes.</p> <p>The wax is sprayed to give an even coat over the surface and is then buffed within 5 – 10 minutes to give a shine.</p>		
<b>Drying Time</b>	<p>The wax film will stay 'open' for between 5 – 10 minutes at 20°C to allow for buffing.</p> <p>Times will vary in colder or warmer conditions.</p> <p>Allow polished wax to harden overnight before putting item into use.</p>		
<b>Coverage</b>	<p>Coverage will vary depending on whether the wax is used on bare or sealed timber and on number of applications used.</p>		
<b>Packaging</b>	<p>Spray Waxes are available in 5 litre and 20 litre containers.</p>		
<b>Physical Constants</b>	<p>VOC level: 630g/ litre.</p>		
<b>Storage</b>	<p>Replace container lid after use and store in a cool place.</p>		
<b>Health and Safety</b>	<p>Refer to Mylands Spray Wax MSDS before use.</p>		

Updated 17.03.2015

For further information visit our website [www.mylands.co.uk](http://www.mylands.co.uk) or contact us: +44 (0)208 670 9161 [sales@mylands.co.uk](mailto:sales@mylands.co.uk)